



DURA-lyst[®] Pt10C

High Performance Platinum Fuel Cell Electrocatalyst

Technical Specification

Catalogue No	Sample Description	XRD, nm	Metal, %	ESA, m²/g
<i>DURA-lyst[®] Pt10C</i>	10% Pt/Vulcan XC72	2.0	Pt: 10	105

Impurities:

Cl⁻ < 300 ppm

Na⁺ & K⁺ < 100 ppm

**Enhanced Metal Stability >200° C; Maximum Electrochemical Surface Area;
Outstanding Platinum Particle Dispersion and Uniformity; Increased Durability
and Performance**

info@sainergytech.com; www.sainergytech.com