



## **DURA-lyst<sup>®</sup> Pt20C**

*High Performance Platinum Fuel Cell Electrocatalyst*

### **Technical Specification**

<b>Catalogue No</b>	<b>Sample Description</b>	<b>XRD, nm</b>	<b>Metal, %</b>	<b>ESA, m<sup>2</sup>/g</b>
<i>DURA-lyst<sup>®</sup> Pt20C</i>	20% Pt/Vulcan XC72	3.0	Pt: 20	95

Impurities:

Cl<sup>-</sup> < 300 ppm

Na<sup>+</sup> & K<sup>+</sup> < 100 ppm

**Enhanced Metal Stability >200° C; Maximum Electrochemical Surface Area;  
Outstanding Platinum Particle Dispersion and Uniformity; Increased Durability  
and Performance**

[info@sainergytech.com](mailto:info@sainergytech.com); [www.sainergytech.com](http://www.sainergytech.com)